

Add  
A,

## CLAIMS

1. Self-adhesive sheet for bonding a floor  
5 covering, especially a carpet, to a floor, especially  
parquet, having a backing layer made in particular of  
polymer film, which is coated on a top surface, facing  
the floor covering, and on a bottom surface, facing the  
10 floor, with a pressure-sensitive adhesive coating and  
which at least on the top surface has a textile  
structure, the pressure-sensitive adhesive coating  
having a different adhesive strength on the two  
surfaces,  
characterized in that  
15 the pressure-sensitive adhesive coating and/or the  
adhesive strength on the bottom surface is a fraction  
of that on the top surface and at least on the bottom  
surface is of substantially planar design.
2. Self-adhesive sheet according to Claim 1,  
20 characterized in that the textile structure has threads  
in a wide-meshed arrangement.
3. Self-adhesive sheet according to Claim 1 or 2,  
characterized in that the textile structure has threads  
running parallel and also threads arranged rhomboidally  
25 at an obtuse angle thereto.
4. Self-adhesive sheet according to one of Claims  
1 to 3, characterized in that the textile structure has  
threads in a thread spacing of from 3 to 30 mm.
5. Self-adhesive sheet for bonding a floor  
30 covering, especially a carpet, to a floor, especially  
parquet, having a backing layer made in particular of  
polymer film, which is coated on a top surface, facing  
the floor covering, and on a bottom surface, facing the  
floor, with a pressure-sensitive adhesive coating, the  
35 pressure-sensitive adhesive coating having a different  
adhesive strength on the two surfaces,  
characterized in that  
the pressure-sensitive adhesive coating and/or the  
adhesive strength on the bottom surface is a fraction

- 10 -

of that on the top surface and at least on the bottom surface is of substantially planar design.

6. Self-adhesive sheet according to one of Claims 1 to 5, characterized that its length and width are  
5 designed so that substantially the entire floor to be covered with the floor covering can be covered extensively.

7. Self-adhesive sheet according to one of Claims 1 to 6, characterized in that the adhesive strength of  
10 the bottom surface features an adhesive force (measured in accordance with DIN 1939) in the order of magnitude of from 0.8 to 5 N, in particular from 1.5 to 3 N and especially from 2.0 to 2.6 N.

8. Self-adhesive sheet according to one of Claims 1 to 7, characterized in that the different adhesive  
15 strength of the two surfaces is brought about by different adhesive application rates, the surface with the greater adhesive strength having a higher adhesive application rate.

20 9. Self-adhesive sheet according to Claim 8, characterized in that the adhesive application rate on the top surface is in the range from 100 to 250 g/m<sup>2</sup> and on the bottom surface is in the range from 5 to 40 g/m<sup>2</sup>, in particular from 8 to 20 g/m<sup>2</sup>.

25 10. Self-adhesive sheet according to one of Claims 1 to 9, characterized in that there is a removable cover film on at least the top surface.

Add  
B<sub>4</sub>